

Operational Standards

OS - 5.2 | Crack Inducers (Self-Levelling Floors)

Revision:

B

Section:

5.0 - Plot Groundworks Stage 1

Visual Aids



Information

Objective	Application
To prevent excessive cracking to self-levelling floors	All internal doorways on plots with a self-levelling concrete finish
Instructions	
- Primary use of propriety crack inducers – install a 40mm high, bottom-Y, crack inducer prior to concrete pour – to all internal doorways - Post pour, strike the concrete to induce a single line crack – this separates the single concrete structure to allow thermal movement, thus, reducing excessive cracking - Consideration of underfloor heating if cutting concrete floor	